

## TEST REPORT

|                      |                       |                    |            |
|----------------------|-----------------------|--------------------|------------|
| <b>Report Ref.</b>   | LEI21042490A Original |                    |            |
| <b>Date Received</b> | 26/04/2021            | <b>Date Issued</b> | 06/05/2021 |

|                                   |   |
|-----------------------------------|---|
| <b>Company Name &amp; Address</b> | Fabisimo Ltd<br>H4 Upper Brents<br>Faversham, ME13 7DZ<br>GBR |
| <b>Contact Name</b>               |   |

|                                 |                              |
|---------------------------------|------------------------------|
| <b>Order Number</b>             | 109001                       |
| <b>Sample Description</b>       | Anti-Microbial Stretch Lycra |
| <b>Ref / Style Number</b>       | 109001                       |
| <b>Colour</b>                   |                              |
| <b>Quality</b>                  |                              |
| <b>Supplier</b>                 | Prinfab                      |
| <b>Batch Number</b>             | 1                            |
| <b>End Use</b>                  | Various                      |
| <b>No Of Samples</b>            | 1                            |
| <b>Quoted Fibre Composition</b> | 95% Polyester 5% Lycra       |
| <b>Retailer</b>                 | General                      |

| Test                           | Method         | Sample | Result |
|--------------------------------|----------------|--------|--------|
| ^Migration of Certain Elements | BS EN71 3:2019 |        | Pass   |

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.  
Tests marked (\*) in this report are not included in our UKAS scope of accreditation.



Stephen Ahern  
(Administrator)



**^Migration of Certain Elements BS EN71 3:2019**

|                                     | Result in mg/kg  | Detection Limit in mg/kg | Requirement in mg/kg |
|-------------------------------------|--|--------------------------|----------------------|
| Sample 1: Anthracite knitted fabric |  |                          |                      |
| Antimony (Sb)                       | 13.8 ppm   | 0.125 ppm                | 560                  |
| Arsenic (As)                        | Not Detected   | 0.125 ppm                | 47                   |
| Barium (Ba)                         | Not Detected   | 0.125 ppm                | 18750                |
| Cadmium (Cd)                        | Not Detected   | 0.125 ppm                | 17                   |
| Chromium (III)                      | Not Detected   | 0.125 ppm                | 460                  |
| Lead (Pb)                           | Not Detected   | 0.125 ppm                | 23                   |
| Mercury (Hg)                        | Not Detected   | 0.0125 ppm               | 94                   |
| Selenium (Se)                       | Not Detected   | 0.125 ppm                | 460                  |
| Aluminium (Al)                      | Not Detected   | 0.125 ppm                | 70000                |
| Boron (B)                           | Not Detected   | 0.125 ppm                | 15000                |
| Cobalt (Co)                         | Not Detected   | 0.125 ppm                | 130                  |
| Copper (Cu)                         | Not Detected   | 0.125 ppm                | 7700                 |
| Manganese (Mn)                      | Not Detected   | 0.125 ppm                | 15000                |
| Nickel (Ni)                         | Not Detected   | 0.125 ppm                | 930                  |
| Strontium (Sr)                      | Not Detected   | 0.125 ppm                | 56000                |
| Tin (Sn)                            | Not Detected   | 0.125 ppm                | 180000               |
| Zinc (Zn)                           | Not Detected   | 0.125 ppm                | 46000                |
| Chromium (VI)                       | Not Detected   | 0.0025 ppm               | 0.053                |
| Organic Tin                         | Not Detected   | 0.125 ppm                | 12                   |
| Remark:                             | mg/kg = milligram per kilogram   |                          |                      |
|                                     | - Unless the test results were marked with # or Δ, 'Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively. |                          |                      |
|                                     | - The new lead migration limit 2.0mg/kg for Category (I), 0.5mg/kg for Category (II) and 23 mg/kg for Category (III) was quoted from directive (EU) 2017/738 amending 2009/48/EC effective from 28 October 2018          |                          |                      |
|                                     | - Organic tin test result was expressed as tributyl tin  |                          |                      |

Overall Test Result: Pass  
Uncertainty: ±9%



| Report Type | Issue Date | Revision Reason         | Revision Description |
|-------------|------------|-------------------------|----------------------|
| Original    | 06-May-21  | Complete Original Issue | N/A                  |

*The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.*

*The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of  $k = 2$ , providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.*

