

TEST REPORT


Report Ref.	LEI23010903A Original		
Date Received	13/01/2023	Date Issued	23/01/2023

Company Name & Address	Fabisimo Ltd Unit E , ME13 7DZ
Contact Name	

Order Number	121001016-1
Sample Description	Organic Optic Interlock Jersey
Ref / Style Number	121001
Colour	
Quality	
Supplier	Prinfab
Batch Number	1
End Use	Various
No Of Samples	1
Quoted Fibre Composition	100% Cotton
Retailer	General

Test	Method	Sample	Result
^Migration of Certain Elements	BS EN71 3:2019		Pass

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.
Tests marked (*) in this report are not included in our UKAS scope of accreditation.



Stephen Ahern
(Administrator)



^Migration of Certain Elements BS EN71 3:2019

	Result in mg/kg	Detection Limit in mg/kg	Requirement in mg/kg
Sample 1: black knitted fabric			
Antimony (Sb)	Not Detected	0.125 ppm	560 ppm
Arsenic (As)	Not Detected	0.125 ppm	47 ppm
Barium (Ba)	0.7 ppm	0.125 ppm	18750 ppm
Cadmium (Cd)	Not Detected	0.125 ppm	17 ppm
Chromium (III)	Not Detected	0.125 ppm	460 ppm
Chromium (VI)	Not Detected	0.0025 ppm	0.053 ppm
Lead (Pb)	Not Detected	0.125 ppm	23 ppm
Mercury (Hg)	Not Detected	0.0125 ppm	94 ppm
Selenium (Se)	Not Detected	0.125 ppm	460 ppm
Aluminium (Al)	3.3 ppm	0.125 ppm	28130 ppm
Boron (B)	Not Detected	0.125 ppm	15000 ppm
Cobalt (Co)	Not Detected	0.125 ppm	130 ppm
Copper (Cu)	1.2 ppm	0.125 ppm	7700 ppm
Manganese (Mn)	1.0 ppm	0.125 ppm	15000 ppm
Nickel (Ni)	Not Detected	0.125 ppm	930 ppm
Strontium (Sr)	3.7 ppm	0.125 ppm	56000 ppm
Tin (Sn)	1.5 ppm	0.125 ppm	180000 ppm
Organic tin	0.4 ppm	0.125 ppm	12 ppm
Zinc (Zn)	21.9 ppm	0.125 ppm	46000 ppm
Remark:	mg/kg = milligram per kilogram		
	- Unless the test results were marked with # or Δ, 'Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.		
	- The new lead migration limit 2.0mg/kg for Category (I), 0.5mg/kg for Category (II) and 23 mg/kg for Category (III) was quoted from directive (EU) 2017/738 amending 2009/48/EC effective from 28 October 2018		
	- Organic tin test result was expressed as tributyl tin		

Overall Test Result: Pass
Uncertainty: ±9%



Report Type	Issue Date	Revision Reason	Revision Description
Original	23-Jan-23	Complete Original Issue	N/A

The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.

