



Client:



Entry No: 55282

Date received: 10/10/2012

Client's Description:



TEST REPORT

Test Required: Flammability in accordance with IMO A.652 (16)
Pre-treatment: None
Conditioning: A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5°C
Date of Test: 19/10/2012

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Butane flame	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: A 20-22kg/m³ non-fire retardant polyurethane foam was used as the filling.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

Geoff Briggs C.Text., A.T.I.
Head of Laboratory
22nd October 2012



1104

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

