


TEST REPORT

Client:



Entry No: 95015

Date received: 05/02/2018

Client's Description:



Test Required: Dimensional Stability to Washing and Drying

Conditioning: In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at $65 \pm 4\%$, Relative Humidity, $20 \pm 2^\circ\text{C}$

Date Tests Completed: 12/02/2018

Dimensional Stability: BS EN ISO 5077: 2008

Washing Procedure: 5 washes in accordance with BS EN ISO 6330: 2012 wash procedure (6N) at 60 Degrees C followed by final line drying.

Warp	-1.5 %
Weft	-1.0 %

Comments

Note: a negative result indicates shrinkage.

Appearance after washing and drying

Washing Procedure: 5 washes in accordance with BS EN ISO 6330: 2012 wash procedure (6N) at 60 Degrees C followed by final line drying.
No change in appearance or change in colour after washing.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank
Technician
19 February 2018

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104