




## TEST REPORT

**Client:**



**Entry No:** 74103

**Date received:** 08/03/2016

**Client's Description:**



**Test Required:** Flammability BS 5867-2 : Type C

**Pre-treatment:** None

**Conditioning:** A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C

**Date Tests Completed:** 14/03/2016

**Method of Test:** BS EN ISO 15025 : 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

**Flame application times 5, 15, 20 and 30 seconds using propane gas**

**As Received**

Both Face and back tested	Fabric Length direction		Fabric Width direction	
	Face 1 ↑	Back 2 ↓	Face 3 →	Back 4 ←
Flame reached an edge (✓ or X)	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X
Duration of flaming (s)	0	0	0	0
Duration of afterglow (s)	0	0	0	0

### Comments

On the basis of the tests carried out this sample of fabric meets the Type C requirements of BS 5867-2: 2008 when tested as received only.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*

Dale Brockbank  
 Materials Testing Manager  
 15 March 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104