




TEST REPORT

Client:



Entry No: 76250

Date received: 02/06/2016

Client's Description:



Test Required: Flammability in accordance with IMO 2010 FTP CODE ANNEX 1 PART 7

Pre-treatment: None

Conditioning: A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-5°C

Date Tests Completed: 08/06/2016

Flame application time: 15 seconds

Mode of Flame Application: Edge ignition

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

| Face | Warp direction | | | | | Weft direction | | | | |
|--------------------------------|----------------|-----|-----|-----|-----|----------------|-----|-----|-----|-----|
| | 1 | 2 | 3 | 4 | 5 | 1 | 2 | 3 | 4 | 5 |
| Specimen number | | | | | | | | | | |
| Flame reached an edge (✓ or X) | X | X | X | X | X | X | X | X | X | X |
| Hole reached an edge (✓ or X) | X | X | X | X | X | X | X | X | X | X |
| Surface Flash (✓ or X) | X | X | X | X | X | X | X | X | X | X |
| Duration of flaming (s) | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 |
| Length of Char (mm) | 136 | 132 | 108 | 127 | 130 | 107 | 119 | 131 | 116 | 129 |
| Ignition of Cotton wool (Y/N) | N | N | N | N | N | N | N | N | N | N |

Mean Char Length: Warp = 127 mm Weft = 120 mm

Comments

On the basis of the tests carried out this sample of fabric meets the performance criteria for curtains and drapes as specified in Clause 3 of IMO 2010 FTP CODE ANNEX 1 PART 7.

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank
 Materials Testing Manager
 08 June 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





Client: [REDACTED]

Entry No:

76250

ANNEX

| | |
|---|------------|
| name and address of the manufacturer / supplier, if known | [REDACTED] |
| type of the material, i.e. curtain, drape, etc | Unknown |
| name and/or identification of the product tested | [REDACTED] |
| description of the sampling procedure, where relevant | Unknown |
| mass per unit area | Unknown |
| thickness | Unknown |
| colour and tone: if the product has a pattern, the representative colour shall be described | White |
| quantity and number of any coating | Unknown |
| method and quantity of fire retardant treatment | Unknown |
| materials of the product such as wool, nylon, polyester, etc., and its composite ratio | Unknown |
| composition of weave: such as plain, weave, twilled | Unknown |
| density (number/inch): the number of threads per inch in both warp and weft | Unknown |
| yarn number count | Unknown |

-----End of Document-----